



ALUMINUM SPECIFICATION

Quality	Value demanded by norm GOST 11069-74	
	A7	A8
Al	Min. 99.7%	Min. 99.8%
Fe	Max. 0.16%	Max. 0.11%
Si	Max. 0.15%	Max. 0.08%
Cu	Max. 0.01%	Max. 0.01%
Zn	max. 0.05%	Max. 0.05%
Ti	max. 0.02%	Max. 0.02%

